



Aquaseal 50

PRODUCT DESCRIPTION

A modified acrylic based compound. An excellent compound for waterproofing with & without membrane.

PRODUCT FEATURES

Aquaseal 50 provides good adhesion to most substrates with ease of application, good flexibility, even at low temperatures, colour versatility & good waterproofing action. When used in conjunction with polyester or polypropylene membrane forms an excellent waterproofing system. Aquaseal 50 is tough & flexible when used with membrane, alkali resistant & displays good weather resistance.

TECHNICAL INFORMATION

Colour: A range of standard colours are available
 Appearance: Smooth finish when dry
 Generic type: Modified acrylic emulsion
 Pigment type: Oxides
 S.G.: ±1.25
 Viscosity: ±120ku
 Spreading rate: ±2.5 litre / m² total membrane system.
 Solvent: Water
 Volume solids: 28%
 Mix ratio: Single pack ready for use
 Packaging: 1 litre, 5 litre, 20 litre plastic containers

SURFACE PREPARATION

Always ensure the substrate is clean, dry and sound prior to application of Aquaseal 50. On very absorbent surfaces it is recommended to apply a first coat of Bonding Liquid. The surface is then to be sanded or wire brushed, prior to application of 1 coat of Bonding Liquid. Abide by recommended over coating times.

APPLICATION

Substrates of mild steel or galvanized steel, need to be clean, dry, degreased, free of loose rust, contaminants prior to applying 1 coat of Etch Primer. Allow to dry for 4 hours at 25°C before applying Aquaseal 50. Stir Aquaseal 50 well before use with a flat paddle.

Roofs and Parapets:

Apply a thick basecoat (± 1 m²/l) of Aquaseal 50 to area slightly wider than the membrane using a brush.

Embed the membrane firmly into the wet Aquaseal 50 to obtain a maximum saturation from below. Ensure a

minimum of 75mm overlap of adjoining lengths of membrane. Remove any air pockets and creases in the membrane. Allow to dry.

Apply a coat of Aquaseal 50 (± 1 m²/l) onto membrane to complete saturation. Allow to dry. Apply 2 further coats of Aquaseal 50 (± 2 m²/l), or 1 coat Aquaseal 50 and 1 coat of an O'Grady's premium acrylic paint.

Allow to dry between coats as recommended.

Walls: Repair any cracks and apply two coats of Aquaseal 50 at the rate of 2m²/l per coat. Aquaseal 50 may be overcoated using an O'Grady's premium acrylic paint.

Airless spray : Not recommended

Conventional spray: Not recommended

Brush & roller: Suitable as supplied

Clean up: Wash immediately with water.

ENVIRONMENT

At no time should paint be applied outdoors in inclement weather or before 9 am and after 2 pm in winter.

Aquaseal 50 will be damaged if subjected to rain prior to curing. It is recommended that application be confined to the following:

Surface temperature: Min. 10°C Max. 40°C

Ambient temperature: Min. 10°C Max. 40°C

Relative humidity: Min.0% Max.85%

Or at least 3°C above Dew point

Do not leave the container open, as a skin quickly forms on the surface of the paint.

DRYING TIME

Drying time is dependent on film thickness, temperature and ventilation. The thicker the film, lower the temperature and less the ventilation the slower the drying time.

Substrate Temp coating	Drying Time	Over
15°C	4 hours	8 hours
20°C	2 hours	4 hours
25°C	1 hours	2 hours
30°C	30 min	1 hour

LIMITATIONS

Sustained cold conditions can result in paint failure. Avoid painting on wet substrates and in wet conditions.

STORAGE AND HANDLING.



Store in cool dry area away from heat, direct sunlight and severe cold. Shelf life: 2 years in original sealed containers.

SAFETY PRECAUTIONS

No known problems resulting from contact with skin, however, remove as soon as possible with soap and water. Avoid ingestion and contact with eyes. If ingested, seek medical attention. Do not induce vomiting. If paint contact is made with eyes, rinse thoroughly with water eyes must be open, and then seek medical attention. Do not smoke when painting
Ensure good ventilation when painting and drying.

KEEP OUT OF REACH OF CHILDREN.

Issue date: January 2017