# **QUICK DRYING ENAMEL**

## PRODUCT DESCRIPTION

A quality, very quick-drying modified alkyd based paint.

## **PRODUCT FEATURES**

Quick drying paint with good gloss, hard & tough finish, making it suitable for light & medium industrial application, including farming implements, tractors & trailers.

## **TECHNICAL INFORMATION**

Colour: A standard range of colours, others

on request

Appearance: Gloss

Generic type: Modified alkyd

Volume solids: ±30%
Viscosity: 78Ku
Recommended DFT: 45 - 55 µm
Spreading rate: 6 - 8m² per litre
Solvent: Industrial Thinners
Mix ratio: Single pack ready for use

Packaging: 1 litre, 5 litre, 20 litre & 200 litre on

request

## SURFACE PREPARATION

All surfaces are to be clean, dry & free from loose paint, oil, grease & other contamination. Rusted metal must be treated & primed prior to application of Quick Dry Enamels.

## **APPLICATION**

Airless spray: No dilution necessary

Nozzle pressure: 100 - 120 bar

Nozzle orifice: 0.015"

Conventional spray: 20 – 25% dilution recommended.

Use Industrial Thinners
Air pressure: 2 - 3 bar
Nozzle orifice: 1.5 – 2mm

Brush and Roller: Suitable as supplied

Clean up: Use Industrial or Lacquer Thinners

for dilution & clean up. Do not use

Mineral Turpentine.

## **ENVIRONMENT**

It is recommended that application be confined to the following:

Surface temperature: Min. 5°C Max. 45°C Ambient temperature: Min. 5°C Max. 45°C Min. 5°C Max. 45°C Min. 0% Min. 0% Max. 45°C Min. 0% Min. 0%

Or at least 3°C above Dew point

#### POT I IFF

Infinite. Air drying after evaporation of thinners. Do not leave the container open.

## **DRYING TIME**

The drying time is dependent on temperature & ventilation. The higher the temperature & the better the ventilation, the shorter the touch dry & hard dry times.

Substrate Temp Touch Dry Hard Dry 25°C 15 minutes 2 hours

## **OVERCOATING TIMES**

Quick Dry Enamels based on styrenated alkyds, have a tendency to wrinkle when over coated after 3 hours & before 24 hours. It is therefore recommended to over coat within 3 hours or after 24 hours at 25°C.

All the above are given as guidelines & can not be assumed to be absolute, as variances will result from different film thickness, environment & temperature.

# **STORAGE & HANDLING**

Store away from sunlight, open flames & severe cold. Shelf life: 1 year in original sealed containers

Flash point: 10°C

## **LIMITATIONS**

Do not overcoat Gloss Enamels with Quick Dry Enamels, as this will result in a wrinkle finish.

Abide by over coating times.

## **SAFETY PRECAUTIONS**

Work with PVC gloves, safety glasses & a respirator. Ensure good ventilation when spraying with Quick Dry Enamels. This product contains flammable materials. Keep away from sparks & open flames. No smoking should be permitted in the area.

KEEP OUT OF REACH OF CHILDREN.

Information Provided is based on Laboratory evaluations and data believed to be reliable.

Recommendations are given in good faith but without warranty. It is the user's responsibility to determine the suitability for their own use.

It is not to be considered a guarantee of the products properties.

For more information contact our Factories: Western Cape: Tel/Fax: (021) 853-8105 Mpumalanga: Tel: (013) 246-2570 Fax: (013) 246-2573